



This information is part of the documentation Technical Foams - Data Sheet Book edition 20

TECHNICAL DATA SHEET

Bulpren S 31048

PROPERTIES	UNIT	METHOD	SPECIFICATIONS
Net density	kg/m ³	ISO 845	26 - 30
Compression Resistance 40 %	kPa	ISO 3386/1	2,0 - 4,0
Ultimate Elongation	%	ISO 1798	350
Tensile Strength	kPa	ISO 1798	200
Visiocell (Cell diameter)	micron	Recticel SS/T.013.4	440 - 520
UNCONTROLLED COPY			

Production plant: We

"All properties and specifications are for technical evaluation and information purposes only and can slightly vary. They do not represent or constitute any representation, warranty or guarantee whatsoever of Recticel and Eurofoam"