

# ETHAFOAM 900

## Brand Polyethylene Foam Plank

ETHAFOAM\* 900 polyethylene foam is a strong, resilient, high-density (140 kg/m<sup>3</sup>), closed-cell foam. It has the highest strength of all current ETHAFOAM brand polyethylene foam products, and is ideally suited as a component

material in products requiring a shock absorbing, vibration dampening, insulating, buoyancy component, and as a material for cushioning components in packaging applications for

impacts or loadings up to 140 kPa.

**Size available (Planks):**  
50 x 600 x 2750 mm

**Colour available:** White

Physical Properties(1)	Test Method	Value
Density	DIN 53420	140 kg/m <sup>3</sup>
Compression Set	DIN 53572 (25% Compression)	< 5%
Compressive Creep @ 140 kPa (1000 hr/23°C)	ASTM D 3575, Suffix BB	< 10%
Compression Deflection @ 10%	ASTM D 3575, Suffix D	400 kPa
@ 25%		500 kPa
@ 50%		700 kPa
Thermal Stability (linear change) 158°F (70°C), 1 week	DIN 53431	< 2%
Water Absorption	DIN 53433	< 1%
Tensile Strength @ peak	DIN 53571	750 kPa
Tensile Elongation (linear change)	DIN 53571	40%
Tear Strength	DIN 53575	6.0 N/mm

(1)The data presented for this product are for unfabricated ETHAFOAM brand polyethylene foam products. While values shown are typical of the product, they should not be construed as specification limits.

– See reverse side for additional properties and product information.

\*Trademark of The Dow Chemical Company.

## Product Features

ETHAFOAM\* 900 polyethylene foam is a durable, high-strength, solid extruded plank that meets or exceeds the requirements for U.S. Federal Standard PPP-C-1752D, Type V and CID A-A – 59136 – Type V – Class 1 – Grade A. As the properties listed on reverse suggest, ETHAFOAM 900 polyethylene foam offers excellent strength, resistance to creep under load, vibration and shock absorbency and water resistance characteristics.

ETHAFOAM 900 polyethylene foam is produced with Dow's patented *RapidRelease* manufacturing process. This new process technology incorporates a patented CFC-

and HCFC-free blowing agent system and an accelerated curing system that reduces residual blowing agents in ETHAFOAM brand polyethylene foam products to trace amounts. ETHAFOAM 900 polyethylene foam is easily fabricated, impervious to most chemicals, non-abrasive and performs consistently over a wide range of temperatures. ETHAFOAM 900 polyethylene foam is also reusable and completely recyclable because it is made out of non-crosslinked polyethylene.

## Flammability

ETHAFOAM 900 polyethylene foam has successfully passed FMVSS 302 flammability

testing, conducted according to the Code of Federal Regulations, CFR 49.

**CAUTION: ETHAFOAM 900 polyethylene foam plank is combustible and should not be exposed to flame or other ignition sources.**

## For Additional Information or Technical Support

For information on products, design assistance and testing services available from Dow, in North America call 1-800-441-4369; in Europe call +49-7227-91-4101.

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Published In January 2001 – The Dow Chemical Company

The Dow Chemical Company, 200 Larkin Center, Midland, MI 48674, USA  
Dow Deutschland GmbH & Co. OHG, Industriestraße 1, D-77836 Rheinmünster, Germany



\*

\*Trademark of The Dow Chemical Company.