


Plastazote®

Low density polyethylene foam
24 kg/m³

**ZOTEGRAM**

Plastazote foam is a closed cell cross-linked polyethylene foam available in sheet form. This data characterises LDPE foam grades LD24 (15kg/m³). The material will thermoform into simple and complex shapes.

Property	Test Method	Units	Typical Value
Density Skin/Skin (s/s)	EN ISO 845 1995 BS 4443 Pt1 : 2 1988 DIN 53420 1978	kg/m ³	24
Recommended operating temperature range	Internal	Max °C	+95
		Min °C	-70
Compression stress - strain characteristics	EN ISO 3386/1 1997 BS 443 Pt1 : 5a 1988		
25% Compression	DIN 53572 1986	kPA	35
40% Compression		kPA	65
50% Compression		kPA	100
60% Compression		kPA	150
Compression set s/s thickness 72 hrs 50% compression 23°C, ½ hr recovery	EN ISO 1856 1996 BS 4443 Pt1 : 6b 1988 DIN 53572 1986	% set	32
Tear strength	EN ISO 1856 1996 BS 4443 Pt6 : 15 1991	N/m	410
Tensile strength	ISO 1798 1983 BS 4443 Pt1 : 3a 1988 DIN 53571 1986	kPA	340
Elongation at break		%	105
Water vapour transmission Temperature = 38°C Relative humidity gradient"	ISO 1663 1981 BS 4370 Pt2 : 8 1993 DIN 53429 1971	µg/m ² /sec	43
Permeability Sample = 25mm thick		ng/Pa/s/m	0.19
Water absorption	DIN 53428 1986		
1 Day		% vol	0.1
7 Days		% vol	0.3
14 Days		% vol	0.4
28 Days		% vol	0.5

Thermal conductivity Tested at mean temp of 10°C	ISO 8302 1991 BS 874 Pt2 : 2.1 1986	W/m.K	0.037
Horizontal burning characteristics	ISO 3582 1978 BS 4735 1974		
Thickness 5mm		mm/sec	2.1
Thickness 13mm		mm/sec	1.4
	FMVSS.302		Pass at 12mm thickness and above
Shore hardness 00 scale (min 10mm c/c thickness)	ISO 868 1985 BS 2782: Pt3 Method 365B : 1992		43